

MARISEAL® 400

Aliphatic Polyurethane Top-Coat, UV-stable Normal Pedestrian Traffic Areas

Product Description

The MARISEAL® 400 is a pigmented, color- and UV-stable, highly permanent elastic, cold applied and cold curing, one component aliphatic polyurethane coating, used as a top-coat for protection over exposed, polyurethane waterproofing coatings.

Cures by reaction with ground and air moisture over a unique moisture triggered chemical reaction.

Protects very efficiently, especially if a dark final color is desired.

Advantages

- Simple application (roller or airless spray).
- One component.
- Increases the abrasion and wear resistance of the waterproofing membrane underneath.
- Provides high sun reflectivity, contributing to thermoinsulation.
- UV and Color stable.
- Gives a glossy and easy-to-clean surface.
- Does not show the chalking effect of aromatic polyurethane coatings.
- Resistant to water, heat and frost.
- Maintains its mechanical properties over a temperature span of -40°C to +90°C.
- The waterproofed surface can be walked on (domestic pedestrian traffic).

Consumption

0,120-0,250 kg/m² in one or two layers.

This coverage is based on practical application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, humidity, application method and finish required can alter consumption.

Uses

- Waterproofing of Roofs
- Waterproofing of Balconies, Terraces and Verandas
- Waterproofing of Pedestrian Decks and Walkways
- Protection of Polyurethane Foam Insulation

Used over the MARISEAL® 250, 250FLASH, 250AQUA, 260, etc. on surfaces, with normal pedestrian traffic (e.g. Roofs, Terraces, Balconies, etc.) that require a glossy, color-stable and non-chalking finish.

Packaging and Colors

The MARISEAL® 400 is supplied in 10 kg, 20 kg pails in white and gray colours.

Other RAL colors may be supplied on demand.

Technical Data

PROPERTY	RESULTS	TEST METHOD
Elongation at break	180%	
Tensile strength	>20 N/mm2	DIN EN ISO 527
Resistance to water pressure	No leak	
Gloss retention after 2000h of accelerated aging (DIN EN ISO 4892-3, 400 MJ/m2)	Good	DIN 67530
Surface chalking after 2000h of accelerated aging (DIN EN ISO 4892-3, 400 MJ/m2)	No chalking observed. Chalking grade 0	DIN EN ISO 4628-6
Adhesion to MARISEAL 250	>2 N/mm2	ASTM D 903
Adhesion to cement	4.5 N/mm2	EN 13892-8
Hardness (Shora A Scale)	85-90	ASTM D 2240 (15’')
Solar Reflectance (SR) White colour	107	ASTM E903-96
UV accelerated ageing, in the presence of moisture	Passed-No significant changes	EOTA TR-010
Hydrolysis (5% KOH, 7days cycle)	No significant elastomeric change	Inhouse Lab
Service Temperature	-40 ° C to +90 ° C	Inhouse Lab
Tack Free time	1-3 hours	Conditions: 20 ° C, 50% RH
Light Pedestrian Traffic Time	12 hours	
Final Curing Time	7 days	
Chemical preoperties	Good resistance against acidic and alkali solutions (5%), detergents, seawater and oils.	

Our technical advice for use, whether verbal, written or in tests, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults; correct application of our products therefore falls entirely within your scope of liability and responsibility. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our R+D department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

Application

Surface Preparation

Careful surface preparation is essential for optimum finish and durability.

The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the membrane. Maximum moisture content should not exceed 5%. Substrate compressive strength should be at least 25MPa, cohesive bond strength at least 1.5MPa. New concrete structures need to dry for at least 28 days. Old, loose coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed.

Waterproofing Membrane

See relevant MARIS POLYMERS product Technical Data Sheet

Top-Coat

Stir MARISEAL[®] 400 well before using.

Apply the MARISEAL[®] 400 by roller, brush or airless spray in one or two layers.

Allow 3-6 hours (not more than 36 hours) to cure, between the two layers.

For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperatures retard cure while high temperature speed up curing. High humidity may affect the final finish.

WARNING: The MARISEAL[®] 400 and/or the MARISEAL[®] SYSTEM is slippery when wet. In order to avoid slipperiness during wet days, sprinkle suitable aggregates onto the still wet coating to create an anti-slip surface. Please contact our R+D Dept. for more details.

WARNING: If on the surface where the MARISEAL[®] system is applied, there are areas with ponding water, they should be cleaned on regular basis to avoid biological and microbial attack.

Storage

Pails should be stored in dry and cool rooms for up to 9 months. Protect the material against moisture and direct sunlight. Storage temperature: 5°-30°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels.

Safety Measures

MARISEAL[®] 400 contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data sheet. PROFESSIONAL USE ONLY.